

TG-A2030 / TG2030 Ultra Soft Thermal Pad

REACH Compliant

RoHS Compliant

UL Compliant

Features


- Low oil-bleed
- Ultra soft and high compressibility
- Electrical insulation
- As a buffer in electronics

Application:

Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

Properties

Contact Pressure, Thermal Impedance, and Deflection



Properties	Unit	TG-A2030 / TG2030	Tolerance	Test Method
Thermal Conductivity	W/m·K	2.1	± 10%	ASTM D5470 Modified
Thickness	mm	0.5~5.0	-	ASTM D374
	inch	0.0197~0.1969	-	ASTM D374
Color	-	White	-	Colorimeter CIE 1976
Flame Rating	-	V-0	-	UL 94
Dielectric Breakdown Voltage	KV/mm	≥16.3	-	ASTM D149
Weight Loss	%	<1	-	ASTM E595 Modified
Density	g/cm ³	2.4	± 5%	ASTM D792
Operating Temperature	° C	-45~+200	-	-
Volume Resistivity	Ohm-m	>10 ¹⁰	-	ASTM D257
Elongation	%	300	-	ASTM D412
Tensile Strength	kgf/cm ²	1	-	ASTM D412
Standard Format	-	Sheet	-	-
Hardness	Shore OO	25	± 10	ASTM D2240

For thicknesses less than 1.0mm, hardness will be adjusted to 50-75 Shore OO to facilitate effective removal of liner during production
 Different tolerances according to the selected thickness
 Die-cut for different shapes